

Product and manufacturer details	
Product Name:	Texan 175 copper spouting
Product Identifier:	TEXCU-COM
Manufacturer’s Name & Address	Refer to table 3 for Continuous Group branded manufacturing locations and/or supply.
Manufacturer’s Email Address	cg@continuous.co.nz
Manufacturer’s Web Address	www.continuous.co.nz
Place of Manufacture	Aotearoa New Zealand
Warnings & Bans	No

Product description

Texan 175mm copper spouting custom length is the main component used in the installation of the Texan 175mm spouting system.

Table 1

System Components	Component - Material
Texan 175 Spouting	Manufactured from 0.55mm-0.60mm DHP Copper – Hard (Grade C12200) that complies with BS EN 1172 as per E1/AS1 Table 6 and AS1566 Manufactured from 0.55mm-0.60mm Copper – ¾ Hard (Grade C12200) copper

Specifications & Installation Requirements

Refer to Texan 175 copper spouting system BPIR:TEXCU-SYS:2023:v1 for full system and installation details.

Table 2

System details	Specification / Installation
Maximum Cross Sectional capacity	20,030mm ²
Flow Capacity	322 litres per minute

Scope of use

Texan 175 copper spouting is an external spouting length designed to collect and channel water that runs off a roof. It is intended that the product is positioned outside of the building envelope.

Limitations of the use of this building product:

1. The product cannot be installed onto fascia or cladding with incompatible materials. The product cannot run-off onto incompatible materials. Material Compatibility, Contact and Run off to be adhered to in accordance with E2/AS1 Table 20, 21 & 22.
2. The product cannot be used as an “Internal gutter” as described in the NZMRP-COP “A gutter positioned inside the building envelope”.
3. The product may require an additional snow support system depending on site location and altitude. *(Reference Section 15 “Snow Loading” NZS3604)*
4. Site locations must be evaluated in areas with high wind &/or salt &/or thermal/industrial atmospheric conditions. These types of locations may require specific engineering design (SED). Designers must consult metal supplier’s information for specific durability requirements (Reference E2/AS1 table 20).

Continuous Group Limited - Building Product Information – Texan 175 copper spouting custom length

Maintenance Requirements

(Link to Care and Maintenance Document below under “Supporting Documentation”)

1. Inspection of the system is required every 3 months to check for buildup of residue and organic matter inside the system.
2. Remove any debris from the inside of the spouting at least every 6 months and immediately after inspection if required.

Relevant building code clauses.

Compliance/Regulation	Detail
E1/AS1 Surface water	Sections: 5.1.4 & 5.2.1
E2/AS1 External Moisture	Table 20
AS/NZS 2179.1.2014	Section: 2.4.2, 3.2.1 and Table 3.1
B2/AS1	Table 1: Durability Requirements of Nominated Building Element

Texan 175 copper spouting contributes to compliance by –

E1/AS1 Section 5.1.4: “In no case shall the cross-sectional area of any gutter be less than 4000 mm².”

- Gutter cross sectional area is 20,030mm².

E1/AS1 Section 5.2.1: “Roof gutter materials shall comply with the standards stated in Table 6”

- Copper sheet used to manufacture gutters meets the standard BS EN 1172 as per E1/AS1 table 6.

E2/AS1 Table 20: “Material Selection”

- The product is classified as “Sheltered” and material selection shown in Table 1 of this BPIR meets the requirements of table 20 for exposure Zones B,C, D & E for “Copper” and “uPVC” materials..

AS/NZS 2179.1.2014 Section 2.4.2: “Copper and copper alloys used for rainwater goods shall comply with AS 1566”

- Spouting is manufactured from copper that complies with AS 1566 as shown in table 1 of this BPIR.

AS/NZS 2179.1.2014 Section 3.2.1 and Table 3.1: “The effective cross-sectional area and minimum base metal thickness (BMT) of shape or sheet for eaves gutters, stop ends and flashing saddles with sole width equal to or less than 200mm shall be specified as in Table 3.1- Gutters less than 10000mm² manufactured from G300 coated steel require a minimum BMT of 0.50mm.”

- Spouting (Gutter) meets the specification required as detailed in table 3.1.

B2/AS1 Table 1: Durability Requirements of Nominated Building Element- requires external gutters to have a durability of 5 Years.

- 20 year warranty is provided with this gutter product provided the maintenance conditions are met.

Continuous Group Limited - Building Product Information – Texan 175 copper spouting custom length**Supporting documentation**

The following additional documentation supports the above statements:

Document name	Weblinks
Texan 175mm Brochure & Specification Document	Texan Spouting Brochure and Specification 2021.pdf
Maintenance Document	Continuous Group Maintenance Document.pdf
Material Compatibility Selection	Continuous Group Material Compatibility - Material Selection v1.pdf
Material Compatibility in Contact	Continuous Group Material Compatibility - Compatibility of materials in contact v1.pdf
Material Compatibility subject to Run Off	Continuous Group Material Compatibility - Compatibility of materials subject to run off v1.pdf
Warranty Document	Continuous Group Warranties

Continuous Group Limited - Building Product Information – Texan 175 copper spouting custom length

Table 3 - Continuous Group manufacturing &/or supply locations

Location	Company details
Continuous Group Northland	Northland Continuous Spouting Ltd. (NZBN# 9429032689105) 2 Sammaree Place, Kerikeri northland@continuous.co.nz
Continuous Group Auckland	Continuous Spouting Auckland Ltd. (NZBN# 9429034029862) 94 Takanini School Road, Takanini, Auckland auckland@continuous.co.nz
Continuous Group Waikato	Continuous Waikato Ltd. (NZBN# 9429030330535) 141 Queens Street, Leamington, Cambridge waikato@continuous.co.nz
Continuous Group Bay of Plenty	Continuous Group BOP Ltd. (NZBN# 9429048508520) 31B Enterprise Drive, Papamoa, Tauranga bop@continuous.co.nz
Continuous Group Gisborne	Streetwise Spouting Ltd. (NZBN# 9429042306276) 4 Leith Street, Gisborne gisborne@continuous.co.nz
Continuous Group Hawke’s Bay	Rooftech Hawke’s Bay Ltd. (NZBN# 9429035443889) 2/7 Cadbury Road, Onekawa, Napier Hawkes_bay@continuous.co.nz
Continuous Group Taranaki	Gutter Solutions Ltd. (NZBN# 9429036739240) 46 Jellicoe Street, Whanganui East taranaki@continuous.co.nz
Continuous Group Whanganui/Manawatu	Gutter Solutions Ltd. (NZBN# 9429036739240) 46 Jellicoe Street, Whanganui East manawatu@continuous.co.nz
Continuous Group Wellington	Wellington Continuous Spouting Ltd. (NZBN# 9429043333974) 8 Hollands Crescent, Naenae, Lower Hutt wellington@continuous.co.nz
Continuous Group Nelson/Marlborough	Top of the South Continuous Spouting Ltd. (NZBN# 9429037834142) 7 Fuji Court, Stoke, Nelson nelson@continuous.co.nz
Continuous Group Westland	Continuous Spouting South Ltd. (NZBN# 9429050107209) 51-57 Revel Street, Hokitika westland@continuous.co.nz
Continuous Group Christchurch/North Canterbury	Continuous Spouting South Ltd. (NZBN# 9429050107209) 16 Westland Place, Izone Industrial Estate, Rolleston canterbury@continuous.co.nz
Continuous Group Mid/South Canterbury	Continuous Spouting South Ltd. (NZBN# 9429050107209) 126 Dobson Street, Ashburton canterbury@continuous.co.nz
Continuous Group Central Otago	Continuous Spouting South Ltd. (NZBN# 9429050107209) 5 Connelly Way, Cromwell otago@continuous.co.nz
Continuous Group Coastal Otago	Continuous Spouting South Ltd. (NZBN# 9429050107209) 8 Benson Close, Mosgiel otago@continuous.co.nz
Continuous Group Southland	Continuous Spouting South Ltd. (NZBN# 9429050107209) 72 Leet Street, Invercargill southland@continuous.co.nz



Continuous Group are members of the NZ Metal Roofing Manufacturers Incorporated and the Roofing Association New Zealand.